



Easier to do Business with...
AGWAY METALS INC.
ANDEX METALS
...pour vous faciliter les Affaires

PRINTED 02.14.14

CondenStop®
Technical Data Sheet
agwaymetals.com

Application: Condensation Control Membrane for use in single & double skin roof systems.

Composition

Fiber	Polyester
Binder	Acrylate / PAN - PMMA - microspheres
Finish	Hotmelt adhesive
Colour	Standard Grey
Release	Foil HDPE-liner
General Product Code	S25122

Absorption & Drying Properties

Absorption at roof pitch	Unit	Value	Conditions
No pitch - flat*	gal/linear ft.	0,083	100%RH, ΔT:17°C
Pitch 2" by 12*	gal/linear ft.	0,057	100%RH, ΔT:17°C
Pitch 7" by 12*	gal/linear ft.	0,043	100%RH, ΔT:17°C
Pitch 12" by 12*	gal/linear ft	0,031	100%RH, ΔT:17°C

*Tested by Fraunhofer, IBP Stuttgart Germany, test report P17-142.1e/2013.

Flame & Thermal Properties

	Unit	Value	Standard
Flame retardancy	Class	I ¹	ASTM 84-04
Reaction to Fire	Class	B-s ¹ , d0 ²	EN 13501-1
Thermal conductivity	(J) W/mK	0,035	
CondenStop® can be qualified as class I 'impervious to mold growth' ³ .			

1 Classification from the Model Building Codes.

2 Testing and classification by Efectis. CondenStop adhered on a profiled sheet can be regarded as A2, s1, d0.

3 Testing and classification by TNO Construction.

Mechanical Properties

Tensile strength:	Unit	Value	Standard
Machine direction	N/5 cm	90	ISO 9073-3
Cross direction	N/5 cm	15	ISO 9073-3
Elongation:	Unit	Value	Standard
Machine direction	%	20	ISO 9073-3
Cross direction	%	80	ISO 9073-3

Dimensions & Packaging

	Unit	Value	Standard
Weight ⁴	lbs/100 ft ²	1.8	ISO 9073-1
Thickness	Inch	0,038	ISO 9073-2
Max. Width	Inch	60	
Core Diameter (ID)	Inch	3	
Roll-length	ft	2600	
Packaging	PE Stretch Foil		

4 Excluding Release Foil.



Easier to do Business with...

AGWAY METALS INC.

ANDEX METALS

...pour vous faciliter les Affaires

PRINTED 02.14.14

CondenStop®

Technical Data Sheet

agwaymetals.com

Reasonable care has been taken in the preparation of this information, but the manufacturer makes no warranty of merchantability or any other warranty, expressed or implied, with respect to this information. The manufacturer makes no representations and assumes no liability for any direct, incidental or consequential damages resulting from its use. Physical property values presented in this document are nominal values obtained by using listed and unlisted methods. Data are subject to normal manufacturing variations and are subject to change without notice. The most recent version of this document supersedes all previous versions. All Rights Reserved. CondenStop and the Stop Sign Logo are registered trademarks of Lantor BV. 2012-11. This document and content may not be reproduced, copied, amended, published and/or otherwise communicated to any third party without Lantor's prior written consent.